



STRINGED INSTRUMENT LACQUER AEROSOL

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

M113-1406

STRINGED INSTRUMENT LACQUER
AEROSOL

PRODUCT DESCRIPTION:

Mohawk Stringed Instrument Lacquer is formulated specifically as a high quality finish for thin, flexible tone-woods such as those used on stringed instruments, made to withstand the expansion and contraction that is characteristic of the unique construction of stringed instruments.

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Nitrocellulose Lacquer
Color	Clear
Sheen	Gloss
Viscosity	N/A
WPG	6.545457959 lbs/gal
Solids by Volume	5.944121178 ±1%
Solids by Weight	8.886229906 ±1%
Flash Point	-76.000000000 °F
HMIS	H: 2, F: 4, R: 0, P: X
Coating VOC (g/l)	701.796530746 g/l
Coating VOC (Lb/Gal)	5.856796778 lbs/gal
Material VOC (g/l)	609.447271792 g/l
Material VOC (Lb/Gal)	5.086102113 lbs/gal
#VOC/#Solid	8.744349188 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.205364549
Spread Rate	95.343703695 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	To touch: 7 minutes; To handle: 15 minutes; To recoat: 1 hour
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Scuff sand between coats with 320 grit as needed to remove fibers and trash.
PH	N/A

DIRECTIONS:

Seal with Mohawk E-Z® Vinyl Sealer (M102-8000). Highlight guitar as desired. SHAKE WELL for one minute after agitator ball rattles. Apply full wet coats with overlapping strokes. Clean spray button. Dry at least 1 hour. Repeat application and dry cycle up to 3 times in one day. Dry overnight. Scuff sand. Repeat until 9-12 coats are applied. Wait at least 1 week after last application. Rub as desired.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.