



LEATHER / VINYL FINISH CLEAR SATIN

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

M109-0630,M109-0630JPN LEATHER / VINYL FINISH CLEAR SATIN

PRODUCT DESCRIPTION:

A flexible and durable coating used to protect and blend in spot repairs on leather and vinyl. The clears are principally used after applying color with Leather Repair Basecoat, Leather Repair Toner and Leather Repair Color Adjuster aerosols.

ADVANTAGES:

- Ø Clear coating – no pigment
- Ø Use to adjust sheen of repair
- Ø Provides added protection from wear
- Ø New! More flexible film

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Solvent base C.A.B./Acrylic lacquer
Color	Clear
Sheen	35° ± 5°
Viscosity	N/A
WPG	6.232579795 lbs/gal
Solids by Volume	4.083261224 ±1%
Solids by Weight	6.078099303 ±1%
Flash Point	-76.000000000 °F
HMIS	H: 2, F: 4, R: 0, P: X
Coating VOC (g/l)	671.698812452 g/l
Coating VOC (Lb/Gal)	5.605621087 lbs/gal
Material VOC (g/l)	515.107203809 g/l
Material VOC (Lb/Gal)	4.298794950 lbs/gal
#VOC/#Solid	11.347784803 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	1.469679687
Spread Rate	65.495510033 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	To touch: 5 minutes; To handle: 15 minutes; To sand and recoat: 30 minutes; To package: Overnight
Oven Dry	User specific
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	As needed for sheen, chemically bonds to itself without sanding. Scuff as needed to smooth coat.
PH	N/A

DIRECTIONS:

Clear coating used to adjust the sheen (shininess) of a leather repair and for added protection. Use on pigmented leather and vinyl only. Always pre-test. Be especially cautious on vinyl. SHAKE WELL. Pick the sheen of Top Coat that matches the leather being repaired. Apply a light, wet coat over the repair area and slightly out in each direction to blend the sheen with the surrounding leather. Do not force dry. Clean spray button immediately by spraying with can upside down until no more product comes out. If clogged, remove spray button with a twisting motion and clean. Gently twist button onto can with opening turned away from you.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.