



PRO-MARK® MAPLE GLAZE 9731232

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

M265-2019,M267-0479,M28 PRO-MARK® MAPLE GLAZE 9731232
5-00270

PRODUCT DESCRIPTION:

The Pro-Mark® capillary marker features excellent flow. Whether you need to touch-up 1 inch or 20 feet, the Pro-Mark® Marker does it the first time and every time. The colors are the most fade resistant, the most resistant to color shift from topcoating and have the best bleed resistance. The nib offers superior flow along with the durability needed to do all normal repair work. Marks equally well with the edge, the bottom or the tip. Good adhesion to most surfaces and resistance to polishes are built into the ProMark® Marker.

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	N/A
Color	N/A
Sheen	N/A
Viscosity	N/A
WPG	7.028908528 lbs/gal
Solids by Volume	9.674175163 ±1%
Solids by Weight	13.414212555 ±1%
Flash Point	53.600000000 °F
HMIS	H: 2, F: 3, R: 0, P: X
Coating VOC (g/l)	728.272967402 g/l
Coating VOC (Lb/Gal)	6.077754139 lbs/gal
Material VOC (g/l)	725.628773229 g/l
Material VOC (Lb/Gal)	6.055687190 lbs/gal
#VOC/#Solid	6.422592353 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.000124682
Spread Rate	155.173769615 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	24 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A
PH	N/A

DIRECTIONS:

For scratches, stroke in direction of scratch. For worn areas, stroke in direction of wood grain. Rub off excess colorant promptly with a soft cloth.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.