



E-Z VINYL BLACK SEALER 275 VOC 5 GAL

TECHNICAL DATA SHEET

| PRODUCT NUMBER | DESCRIPTION |
|---------------------|--------------------------------------|
| M612-3067,M612-3068 | E-Z VINYL BLACK SEALER 275 VOC 5 GAL |

PRODUCT DESCRIPTION:

E-Z Vinyl® Sealer is designed for use in high contact areas where improved durability, water resistance, and adhesion are critical. A key advantage is improved system flexibility. When properly applied under Mohawk pre-catalyzed or post-catalyzed systems, the system passes and /or exceeds KCMA testing. No catalyst needed. Ready to spray viscosity.

ADVANTAGES:

1. Quick drying
2. Easy to sand
3. Excellent adhesion
4. 275 VOC compliant

PHYSICAL PROPERTIES AND SPECIFICATIONS

| | |
|---------------------------|---|
| Technology | Solvent base pigmented sealer |
| Color | Black |
| Sheen | N/A |
| Viscosity | 38 seconds, Zahn #1 sig @ 77° F |
| WPG | 9.305838777 lbs/gal |
| Solids by Volume | 22.225959620 ±1% |
| Solids by Weight | 39.791833981 ±1% |
| Flash Point | -4.000000000 °F |
| HMIS | H: 2, F: 3, R: 0, P: X |
| Coating VOC (g/l) | 253.849049415 g/l |
| Coating VOC (Lb/Gal) | 2.118480542 lbs/gal |
| Material VOC (g/l) | 80.301704729 g/l |
| Material VOC (Lb/Gal) | 0.670152594 lbs/gal |
| #VOC/#Solid | 0.180977349 lbs/lbs solid |
| VHAP Ratio (#VHAP/#Solid) | 0.062417021 |
| Spread Rate | 356.504392305 sq. ft./gal @ 1.0 mil DFT (no loss) |
| Catalyst/Ratio | N/A |
| Reducer | Ready to spray; M650-0017 Acetone as needed |
| Retarder | M612-1047 Retarder for low VOC coatings; 10% maximum addition by volume |
| AirDry | To touch: 10 min; To recoat: 30 - 45 min |
| Oven Dry | User specific |
| Shelf-Life (Unopened) | 12 months |
| Pot-Life (Catalyzed) | N/A |
| Recoat Instruction | If two coats are needed, sand the first coat aggressively with 220 grit sandpaper. Apply the second coat in a light, even coat of no more than 3-4 wet mils |
| PH | N/A |

DIRECTIONS:

Stir product thoroughly after opening and frequently throughout use. E-Z Vinyl® Black Sealer is manufactured at spray viscosity and should be applied in light, even coats of no more than 3-4 wet mills. If two coats are needed, sand the first coat aggressively with 220 grit sandpaper. Apply the second coat in a light, even coat of no more than 3-4 wet mills, allow to dry and sanded with 320 grit sandpaper, taking care not to sand thro the edges. All Mohawk 275 VOC formulations are high solids products, which build very quickly. Total film build of the entire system, including topcoats, should not exceed 4 dry mills. Excessive build may lead to poor adhesion, cracking or cold check problems. Remove sanding dust before topcoat application. Mohawk Retarder for Low VOC Coatings (M612-1047) is recommended if a flow enhancer is needed. 10% maximum addition by volume.

Mohawk E-Z Vinyl® White Sealer is manufactured at spray viscosity. If further reduction is required, Mohawk Acetone (M650-001) is recommended. Recoating E-Z Vinyl™ Black Sealer (M612-306) should take place after 30-45 minutes of dry time or after a fresh sanding. Stainless spray equipment is strongly recommended. Total dry film of the entire system, including topcoats, should not exceed 4 mils. All products should be stirred properly before being used and also continuously agitated while in use to insure product consistency from start to finish. Filtering at every opportunity is suggested. The system should be pre-tested on the wood to be finished under application conditions. Mixing with other products or finish systems is not recommended. Mohawk Finishing Products will not be held liable for finish failure resulting from mixing products or systems. This product is formulated for interior applications and is not recommended or tested for exterior use.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.