



FINISHER'S CHOICE WHITE SANDING SEALER 55 GAL

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

M612-35007,M612-35008,M 612-35009,MA612-35007,M
A612-35008 FINISHER'S CHOICE WHITE SANDING SEALER 55 GAL

PRODUCT DESCRIPTION:

Finisher's Choice™ White Sanding Sealer is a maximum 275 g/l VOC pigmented lacquer sanding sealer. This high quality white colored sanding sealer is used to seal off wood or MDF surfaces before applying colored or clear topcoats. Our unique formulation sprays on wet, dries fast, is easy to sand and has excellent hold out properties. It is a high solids formulation that helps you save time and money by getting the build you need with less application. 2 coats are adequate for hide and build. Topcoat with Finisher's Choice™ White Lacquer of the desired sheen. Solids: 50%.

ADVANTAGES:

1. Quick dry
2. Excellent flow out
3. Excellent Hide
4. Excellent sanding properties

PHYSICAL PROPERTIES AND SPECIFICATIONS

| | |
|---------------------------|---|
| Technology | 275 VOC nitrocellulose white sanding sealer |
| Color | White |
| Sheen | N/A |
| Viscosity | 60-70 KU (Stormer type) @ 77° F |
| WPG | 9.641970001 lbs/gal |
| Solids by Volume | 29.395114961 ±1% |
| Solids by Weight | 50.516114785 ±1% |
| Flash Point | -4.000000000 °F |
| HMIS | H: 2, F: 3, R: 0, P: X |
| Coating VOC (g/l) | 240.907247817 g/l |
| Coating VOC (Lb/Gal) | 2.010475588 lbs/gal |
| Material VOC (g/l) | 98.170863384 g/l |
| Material VOC (Lb/Gal) | 0.819278482 lbs/gal |
| #VOC/#Solid | 0.168203811 lbs/lbs solid |
| VHAP Ratio (#VHAP/#Solid) | 0.012909514 |
| Spread Rate | 471.497643974 sq. ft./gal @ 1.0 mil DFT (no loss) |
| Catalyst/Ratio | N/A |
| Reducer | 20% M650-0017 Acetone or other exempt reducer, or as needed |
| Retarder | Retarder For Low Voc Coatings M612-1047; maximum addition 20% by volume |
| AirDry | Dry to touch 10 minutes; Dry to sand and recoat 30 to 45 minutes |
| Oven Dry | User specific |
| Shelf-Life (Unopened) | 36 months |
| Pot-Life (Catalyzed) | N/A |
| Recoat Instruction | Sand immediately before topcoating |

DIRECTIONS:

Mohawk Finisher's Choice™ White Sanding Sealer (MA612-3500) is a high solids, high viscosity formulation that offers excellent hiding properties. Depending on spray equipment, use Mohawk Acetone (M650-001) to reduce viscosity by 20% or as needed. Stir thoroughly before using. Seal with a full wet coat of Finisher's Choice™ White Sanding Sealer (MA612-3500), and allow to dry for 30-45 minutes. Sand thoroughly with 240 or finer grit stearated sandpaper, and remove dust before topcoat application. Mohawk Retarder for Low VOC Coatings (MA612-1047) can be used to improve flow out and levelness of the coating; maximum additon 20% by volume. Clean up with Mohawk Acetone (M650-001).

Note: Recoating Finisher's Choice™ White Sanding Sealer should take place after 30-45 minutes of dry time. Sand first coat of sealer aggressively then scuff sand second coat to prevent excessive build of sealer prior to top coating with Finisher's Choice™ White Lacquer (MA612-35XX). Stainless spray equipment is strongly recommended. Total dry film of the entire system, including topcoats, should not exceed 4 mils. All products should be stirred properly before being used and also continuously agitated while in use to insure product consistency from start to finish. Filtering at every opportunity is suggested. The system should be pre-tested on the wood to be finished under application conditions. Mixing with other products or finish systems is not recommended. Mohawk Finishing Products will not be held liable for finish failure resulting from mix products or systems. This product is formulated for interior applications and is not recommended or tested for exterior use.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.