



PATCHAL® PUTTY CHERRY 4 OZ

TECHNICAL DATA SHEET

PRODUCT NUMBER

M734-0007

DESCRIPTION

PATCHAL® PUTTY CHERRY 4 OZ

PRODUCT DESCRIPTION:

Patchal® Putty is an easy to use filler designed for use on small cosmetic repairs only. Patchal® Putty is designed to be used on finished wood to fill nail holes, miter joints and cabinet seams. Patchal® Putty may be topcoated with lacquer for increased durability.

70+ Individual Colors, 2 – 24 pack assortments

ADVANTAGES:

1. Fast easy application and simple clean up
2. Superior color selection matched to current industry trends
3. Fade resistant, non-bleeding permanent colors
4. May be topcoated immediately
5. Easy open packaging keeps putty fresh

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Colored wax filler
Color	Red Brown
Sheen	N/A
Viscosity	Paste
WPG	10.186754445 lbs/gal
Solids by Volume	49.676693435 ±1%
Solids by Weight	66.835924389 ±1%
Flash Point	106.000000000 °F
HMIS	H: 2, F: 1, R: 0, P: X
Coating VOC (g/l)	404.813321922 g/l
Coating VOC (Lb/Gal)	3.378342947 lbs/gal
Material VOC (g/l)	404.813321967 g/l
Material VOC (Lb/Gal)	3.378342947 lbs/gal
#VOC/#Solid	0.496201345 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.000000000
Spread Rate	796.814162697 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	12 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A
PH	N/A

DIRECTIONS:

Fill defect or seam with Patchal® Putty using your fingertip. Remove excess putty with a cloth or with the edge of a plastic card. Patchal® Putty is to be used for small cosmetic repairs only. Topcoat Patchal® Putty with aerosol lacquer for increased durability. Not recommended for tabletops or other wearing surfaces.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.