



## BK-SCRATCH OFF UNLABELED

### TECHNICAL DATA SHEET

#### PRODUCT NUMBER

#### DESCRIPTION

M840-2002,M840-2004,M840-2005,M840-2007,U840-2002 BK-SCRATCH OFF UNLABELED

#### PRODUCT DESCRIPTION:

MOHAWK SCRATCH-OFF™ FOR DARK FINISHES is perfect for antiques and other interior woodwork. Use to hide minor scratches and revive or polish the finish of dark colored woods such as Walnut and Mahogany.

#### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Pigmented Oil Stain
Color	Brown
Sheen	NA
Viscosity	25-30" sig Zahn 1
WPG	7.283036111 lbs/gal
Solids by Volume	2.881000804 ±1%
Solids by Weight	3.431109901 ±1%
Flash Point	120.200000000 °F
HMIS	H: 1, F: 3, R: 0, P: X
Coating VOC (g/l)	842.754714177 g/l
Coating VOC (Lb/Gal)	7.033154025 lbs/gal
Material VOC (g/l)	842.754714200 g/l
Material VOC (Lb/Gal)	7.033154025 lbs/gal
#VOC/#Solid	28.145087986 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.002297663
Spread Rate	46.211207599 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	24 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A
PH	N/A

Hydrotreated Heavy Alkanes - CAS 64742-52-5 - solvent  
C8-9 Alkane/Cycloalkane - CAS 64742-49-0 - solvent  
C9-12 Light Alkanes – CAS 64742-88-7 - solvent  
Asphalt, oxidized - CAS 64742-93-4 - colorant  
Hydrotreated Light Alkanes - CAS 64742-47-8 - solvent  
Dinonylnaphthalenesulfonic Acid - CAS 25322-17-2 - anti-static

Proprietary Anti-Static - CAS not available - anti-static  
Benzene - CAS 71-43-2 - not intentionally added

---

**DIRECTIONS:**

SHAKE WELL BEFORE USING. Apply Scratch-Off™ to a soft cloth. Wipe evenly over the entire surface. Wipe dry with another cloth.

*The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.*

*Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.*

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.