



ENDURAGREEN® INTERIOR WHITE ACRYLIC 10 SHEEN

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

A28W3510BPR1,
A28W3510WP5S

ENDURAGREEN® INTERIOR WHITE
ACRYLIC 10 SHEEN

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Waterborne acrylic
Color	White
Sheen	Flat
Viscosity	15-20 #3 Zahn Cup
WPG	9.77 lbs/gal
Solids by Volume	27.41 ±1%
Solids by Weight	37.89 ±1%
Flash Point	200.00 °F
HMIS	H: 2, F: 1, R: 0, P: X
Coating VOC (g/l)	100.22 g/l
Coating VOC (Lb/Gal)	0.84 lbs/gal
Material VOC (g/l)	30.94 g/l
Material VOC (Lb/Gal)	0.26 lbs/gal
#VOC/#Solid	0.07 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.01
Spread Rate	439.62 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	None
Reducer	Water if needed
Retarder	Propylene Glycol - 1-3 oz per gallon
Air Dry	30 minutes to sand
Oven Dry	Customer specific
Shelf-Life (Unopened)	12 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Dry minimum 1 hour, scuff sand prior to recoat with 320 grit paper.
PH	N/A

1 freeze/thaw cycle. If product freezes, allow 48 to 72 hours to recover.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. SDS and CPDS sheets are available upon request. Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data. The following definitions are being utilized for HAP content: "HAPS-Compliant": < or = .8 lb. HAPS/Lb. Solids; "Low-HAPS": <.5 Lb. HAPS/Lb. Solids; "Ultra-Low-HAPS": <.2 Lb. HAPS/Lb. Solids; "HAPS-Free": <0.00 Lb. HAPS/Lb. Solids. HAP content is based upon the presence of HAP compounds utilizing limits as defined in 29 CFR 1910.1200. Manufacturer assumes no liability for use of this information which is intended to serve as a general guide.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Finishworks™, Division of RPM Industrial Coatings Group, Inc. All rights reserved.