



# CAB/ACRYLIC CLEAR TOPCOAT 40 SHEEN - 275 VOC

## TECHNICAL DATA SHEET

### PRODUCT NUMBER

### DESCRIPTION

L50C7240L1,L50C7240L5/S CAB/ACRYLIC CLEAR TOPCOAT 40 SHEEN  
- 275 VOC

### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Solvent based C.A.B / Acrylic
Color	Clear
Sheen	40° ± 2
Viscosity	34" ± 1 Zahn 1 sig @ 77° F 50% relative humidity
WPG	7.59 lbs/gal
Solids by Volume	16.35 ±1%
Solids by Weight	20.35 ±1%
Flash Point	-4.00 °F
HMIS	H: 2, F: 3, R: 0, P: X
Coating VOC (g/l)	274.20 g/l
Coating VOC (Lb/Gal)	2.29 lbs/gal
Material VOC (g/l)	66.02 g/l
Material VOC (Lb/Gal)	0.55 lbs/gal
#VOC/#Solid	0.36 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.01
Spread Rate	262.26 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	Ready to spray; T84C0033 Acetone as needed
Retarder	T84C0521 Retarder for Low VOC Coatings; 5% max
Air Dry	To touch: 10 min, To handle: 20 min, To recoat: 30-45 min
Oven Dry	Flash dry before applying heat, 120° max
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Scuff sand with 320 grit stearated sand paper and remove sanding dust before recoat
PH	N/A

Maximum dry film thickness for total system not to exceed 4 dry mils

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. SDS and CPDS sheets are available upon request. Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data. The following definitions are being utilized for HAP content: "HAPS-Compliant": < or = .8 lb. HAPS/Lb. Solids; "Low-HAPS": <.5 Lb. HAPS/Lb. Solids; "Ultra-Low-HAPS": <.2 Lb. HAPS/Lb. Solids; "HAPS-Free": <0.00 Lb. HAPS/Lb. Solids. HAP content is based upon the presence of HAP compounds utilizing limits as defined in 29 CFR 1910.1200. Manufacturer assumes no liability for use of this information which is intended to serve as a general guide.

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Finishworks™, Division of RPM Industrial Coatings Group, Inc. All rights reserved.