

## TONE FINISH TONER STORM

PRODUCT NUMBER

**DESCRIPTION** 

M101-0012

TONE FINISH TONER STORM

PRODUCT DESCRIPTION:

TECHNICAL DATA SHEET

N/A

## PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology         N/A           Color         BLACK           Sheen         N/A           Viscosity         N/A           WPG         6.563524130 lbs/gal           Solids by Volume         6.383902620 ±1%           Solids by Weight         9.487215920 ±1%           Flash Point         -76.000000000 °F           HMIS         H: 2, F: 4, R: 0, P: X           Coating VOC (g/l)         705.539394890 g/l           Coating VOC (Lb/Gal)         5.88032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Retarder         N/A           AirDry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A           PH         N/A		
Sheen         N/A           Viscosity         N/A           WPG         6.563524130 lbs/gal           Solids by Volume         6.383902620 ±1%           Solids by Weight         9.487215920 ±1%           Flash Point         -76.00000000 °F           HMIS         H: 2, F: 4, R: 0, P: X           Coating VOC (g/l)         705.59394890 g/l           Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (tb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#V/HAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           AirDry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Technology	N/A
Viscosity         N/A           WPG         6.563524130 lbs/gal           Solids by Volume         6.383902620 ±1%           Solids by Weight         9.487215920 ±1%           Flash Point         -76.000000000 °F           HMIS         H: 2, F: 4, R: 0, P: X           Coating VOC (g/l)         705.539394890 g/l           Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           AirDry         N/A           AirDry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Color	BLACK
WPG         6.563524130 lbs/gal           Solids by Volume         6.383902620 ±1%           Solids by Weight         9.487215920 ±1%           Flash Point         -76.000000000 °F           HMIS         H: 2, F: 4, R: 0, P: X           Coating VOC (g/l)         705.539394890 g/l           Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Sheen	N/A
Solids by Volume         6.383902620 ±1%           Solids by Weight         9.487215920 ±1%           Flash Point         -76.000000000°F           HMIS         H: 2, F: 4, R: 0, P: X           Coating VOC (g/l)         705.539394890 g/l           Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           AirDry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Viscosity	N/A
Solids by Weight         9.487215920 ±1%           Flash Point         -76.000000000 °F           HMIS         H: 2, F: 4, R: 0, P: X           Coating VOC (g/l)         705.539394890 g/l           Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	WPG	6.563524130 lbs/gal
Flash Point         -76.00000000 °F           HMIS         H: 2, F: 4, R: 0, P: X           Coating VOC (g/l)         705.539394890 g/l           Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Solids by Volume	6.383902620 ±1%
HMIS         H: 2, F: 4, R: 0, P: X           Coating VOC (g/l)         705.539394890 g/l           Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Solids by Weight	9.487215920 ±1%
Coating VOC (g/l)         705.539394890 g/l           Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           Retarder         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Flash Point	-76.000000000 °F
Coating VOC (Lb/Gal)         5.888032605 lbs/gal           Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	HMIS	H: 2, F: 4, R: 0, P: X
Material VOC (g/l)         658.217550919 g/l           Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Coating VOC (g/I)	705.539394890 g/l
Material VOC (Lb/Gal)         5.493111269 lbs/gal           #VOC/#Solid         8.821501764 lbs/lbs solid           VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           Retarder         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Coating VOC (Lb/Gal)	5.888032605 lbs/gal
#VOC/#Solid 8.821501764 lbs/lbs solid  VHAP Ratio (#VHAP/#Solid) 0.664336339  Spread Rate 102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)  Catalyst/Ratio N/A  Reducer N/A  Retarder N/A  AirDry N/A  Oven Dry N/A  Shelf-Life (Unopened) 36 months  Pot-Life (Catalyzed) N/A  Recoat Instruction N/A	Material VOC (g/l)	658.217550919 g/l
VHAP Ratio (#VHAP/#Solid)         0.664336339           Spread Rate         102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)           Catalyst/Ratio         N/A           Reducer         N/A           Retarder         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Material VOC (Lb/Gal)	5.493111269 lbs/gal
Spread Rate 102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)  Catalyst/Ratio N/A  Reducer N/A  Retarder N/A  AirDry N/A  Oven Dry N/A  Shelf-Life (Unopened) 36 months  Pot-Life (Catalyzed) N/A  Recoat Instruction N/A	#VOC/#Solid	8.821501764 lbs/lbs solid
Catalyst/Ratio         N/A           Reducer         N/A           Retarder         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	VHAP Ratio (#VHAP/#Solid)	0.664336339
Reducer         N/A           Retarder         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Spread Rate	102.397798025 sq. ft./gal @ 1.0 mil DFT (no loss)
Retarder         N/A           AirDry         N/A           Oven Dry         N/A           Shelf-Life (Unopened)         36 months           Pot-Life (Catalyzed)         N/A           Recoat Instruction         N/A	Catalyst/Ratio	N/A
AirDry N/A Oven Dry N/A Shelf-Life (Unopened) 36 months Pot-Life (Catalyzed) N/A Recoat Instruction N/A	Reducer	N/A
Oven Dry N/A Shelf-Life (Unopened) 36 months Pot-Life (Catalyzed) N/A Recoat Instruction N/A	Retarder	N/A
Shelf-Life (Unopened) 36 months  Pot-Life (Catalyzed) N/A  Recoat Instruction N/A	AirDry	N/A
Pot-Life (Catalyzed) N/A Recoat Instruction N/A	Oven Dry	N/A
Recoat Instruction N/A	Shelf-Life (Unopened)	36 months
	Pot-Life (Catalyzed)	N/A
PH N/A	Recoat Instruction	N/A
	PH	N/A

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Wood Finishes Group, Inc.; P.O. Box 22000 Hickory, NC 28603; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.