



# GUITAR TONER LACQUER AEROSOL- ENCORE BROWN

## TECHNICAL DATA SHEET

PRODUCT NUMBER	DESCRIPTION
M113-1201	GUITAR TONER LACQUER AEROSOL- ENCORE BROWN

### PRODUCT DESCRIPTION:

Toner designed for coloring stringed instruments. Dye concentration is fine tuned for applying a transparent stain and/or creating a sunburst effect.

### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Nitrocellulose Lacquer
Color	Brown
Sheen	Gloss
Viscosity	N/A
WPG	6.382940708 lbs/gal
Solids by Volume	4.646983347 ±1%
Solids by Weight	7.806119140 ±1%
Flash Point	-76.000000000 °F
HMIS	H: 2, F: 4, R: 0, P: X
Coating VOC (g/l)	673.027698913 g/l
Coating VOC (Lb/Gal)	5.616708385 lbs/gal
Material VOC (g/l)	502.077486214 g/l
Material VOC (Lb/Gal)	4.190054631 lbs/gal
#VOC/#Solid	8.409374625 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.876294141
Spread Rate	74.537612886 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	To touch: 7 minutes; To handle: 15 minutes; To package: overnight
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	As needed for color. Allow to dry to a tack between coats.
PH	N/A

### DIRECTIONS:

Seal with Mohawk E-Z Vinyl® Sealer (M102-8000). SHAKE WELL before using. Can temperature should be between 65° and 90° F. Apply fine mist coats evenly over the surface to create a transparent stain. Apply a sunburst effect by spraying near the edge with the nozzle pointed away from the center of the instrument. Add the color slowly until the desired depth of color is achieved. Dry 1 hour. Topcoat with Mohawk Stringed Instrument Lacquer (M113-1406).

*The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Wood Finishes Group, Inc.; P.O. Box 22000 Hickory, NC 28603; Phone: 1-800-545-0047; Fax: 1-800-721-1545.*

*Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.*

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.