



# ENDURAGREEN WATERBORNE EXTENDER QT

## TECHNICAL DATA SHEET

PRODUCT NUMBER	DESCRIPTION
M645-7006	ENDURAGREEN WATERBORNE EXTENDER QT

### PRODUCT DESCRIPTION:

EnduraGreen® Extender is an additive that can be used in any of EnduraGreen® waterborne products to increase the dry and/or working time. Use this additive when working on large surfaces or in warm to dry climates. EnduraGreen® Extender does increase the recoat window, allow additional time before topcoating or recoating.

### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	N/A
Color	N/A
Sheen	N/A
Viscosity	N/A
WPG	8.421562311 lbs/gal
Solids by Volume	0.004953583 ±1%
Solids by Weight	0.007123965 ±1%
Flash Point	210.200000000 °F
HMIS	H: 1, F: 0, R: 0, P: X
Coating VOC (g/l)	1036.290205748 g/l
Coating VOC (Lb/Gal)	8.648291738 lbs/gal
Material VOC (g/l)	259.089653196 g/l
Material VOC (Lb/Gal)	2.162215656 lbs/gal
#VOC/#Solid	3603.999099973 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.000000000
Spread Rate	0.079445366 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A
PH	N/A

### DIRECTIONS:

EnduraGreen® Extender can be initially added at 1.5% by volume, 2.0 oz per gallon, directly to the EnduraGreen® product. Stir thoroughly after adding, making sure it's fully incorporated. If more is needed it can be added up to 4.5% by volume, 6.0 oz per gallon. EnduraGreen® Extender does reduce the viscosity, adjust equipment if needed. EnduraGreen® Extender can be used in VOC regulated areas and will remain in compliance if used according to directions, 6 oz per gallon max level.

*The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Wood Finishes Group, Inc.; P.O. Box 22000 Hickory, NC 28603; Phone: 1-800-545-0047; Fax: 1-800-721-1545.*

*Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.*

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.