



# 8XWIPING STAIN LIGHT GOLDEN OAK QT

## TECHNICAL DATA SHEET

PRODUCT NUMBER	DESCRIPTION
MA240-4156	8XWIPING STAIN LIGHT GOLDEN OAK QT

### PRODUCT DESCRIPTION:

Mohawk Wiping Stains are perfect for any interior wooden surface and are available in 24 stock colors. Wiping Stains are ready to use, semi-transparent, pigment based stains that are fade resistant, easy to stir, non-settling formulas. Only 60 minutes drying time is needed before a lacquer sealer coat can be sprayed. Wiping Stains are easy to control because there's less lapping and may be applied by spray, brush or cloth. Wiping Stains are an ideal uniforming stain when applied over dye stains.

### ADVANTAGES:

1. Fade resistant, non-bleeding permanent colors.
2. Application by spray, rag or brush.
3. Ultra fine ground pigments for maximum color yield.
4. Seal coat may be applied over stain after 1 hour of dry time.
5. 240 VOC Compliant

### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Oil Based Wiping Stain
Color	Brown
Sheen	N/A
Viscosity	N/A
WPG	8.497797104 lbs/gal
Solids by Volume	55.800267283 ±1%
Solids by Weight	64.753943737 ±1%
Flash Point	-4.000000000 °F
HMIS	H: 2, F: 3, R: 0, P: X
Coating VOC (g/l)	240.706742158 g/l
Coating VOC (Lb/Gal)	2.008802281 lbs/gal
Material VOC (g/l)	189.947899241 g/l
Material VOC (Lb/Gal)	1.585197697 lbs/gal
#VOC/#Solid	0.288078503 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.012960497
Spread Rate	895.036287219 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	To touch: 10 minutes, To handle: 20 minutes, To topcoat: 60 minutes
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A
PH	N/A

**DIRECTIONS:**

**STIR WELL BEFORE USING.** Apply generously by wiping, brushing, or spraying. Allow to flash off momentarily, then use a clean absorbent cloth to remove excess. Allow to dry approximately one hour before sealing or top coating. May be intermixed with other MA240 stains to create custom colors. Use MA240-50007 Wiping Stain Base to reduce color strength if desired or as a pre-stain conditioner to control stain color penetration and color development.

*The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Wood Finishes Group, Inc.; P.O. Box 22000 Hickory, NC 28603; Phone: 1-800-545-0047; Fax: 1-800-721-1545.*

*Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.*

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.